



# **MIROCAT PC 3241 Clear Sealer**

MIROCAT PC 3241 is a single pack, pre-catalysed sanding sealer that provides an excellent base for a range of Mirotone topcoats. The rapid drying time and excellent free sanding ensure reduced down time between coats, whilst the excellent build reduces the number of topcoats required.

## **Product Advantages**

- High build provides improved hold up and reduces the number of coats required.
- Easy to use, achieve an excellent finish with minimal effort.
- Fast drying allows early sanding which minimises production time.

## **Typical Applications**

Interior use only. Ideal for domestic furniture, children's toys and furniture, picture frames, musical instruments, joinery and antique restoration.

#### **Product Properties**

## **Typical Properties**

Build: High Colour: Turbid in can, dries clear

Sandability: Excellent Gloss: N/A

Vertical Hold Up: Very Good
Solvent Resistance: Good
Water Resistance: Good
Levelling & Flow: Excellent
Sink Back: Minimal

**Coverage:** 6 m² per litre at 150 micron wet film build. This is dependent on the application equipment / gun set up and the article being coated.

Thinning: Thin up to 10% with MIROSOL 1222 or 1220 (Fast), 1294 (Medium), 1242 (Slow)

**Application Viscosity:** 50-60 seconds BS4 Flow Cup at 25°C.

Wet Film Thickness (WFT): 150-200 microns per coat.

## **Application Methods:**

Suction Gun: Use 1.5 to 2mm (59-79 thou) orifice with 350-400kpa (50-55 psi).

Pressure Pot: Use 1.5 to 2mm (59-79 thou) orifice with pressure pot air-cap. Gun pressure 350-

400kpa (50-55 psi) and a pot pressure of 45kpa (6 psi) max.

Airless Spray: Use 0.23 to 0.33mm (9-13 thou) orifice, 15cm fan (dependent on job) with

regulated pump pressure of 350-400kpa (50-55 psi).

Air Mix Guns: Settings similar to airless spray with the air-assisted regulator pressure at 70-

90kpa (10-15psi).

MIROCAT PC 3241 Issued 25<sup>th</sup> September 2019 Page 1

The information in this data sheet represents typical values. Application variables affect product performance therefore this information should be used as a guide. The user must satisfy themselves as to the suitability of this product for their requirements. Mirotone assumes no liability for use of this information.

**Drying:** Dust Free: 15-20 minutes

Touch Dry: 25-30 minutes Sanding: 2-3 hours

Topcoat: Within 24 hours of sanding

Block Stacking: 24 hours

Low temperatures and heavy wet film thickness will retard drying times.

Recommended Topcoats: MIROCAT PC 3210 Clear Topcoat

MIROCAT PC 3220 Clear Topcoat MIROTHANE PU 5588 Clear Topcoat

Application Equipment Clean Up: Clean all equipment using MIROSOL 1222 or 1286 Thinner

Shelf Life: 36 months

Packaging: 20 litres

#### Refer to the MIROCAT PC Product Information Guide for more information.

#### **Health & Safety**

Before handling, refer to the Material Safety Data Sheet for health and safety information. Ensure that all personnel using this product have read and understood this data sheet and the associated MSDS and packaging label before using this product.

Mirotone Pty Ltd Australia (Head Office)

ABN 40 000 041 136 21 Marigold Street, Revesby NSW 2212 Australia P +61 2 9795 3700 F +61 2 9771 3601 sales@mirotone.com.au Mirotone (NZ) Ltd New Zealand (Head Office)

32 Cryers Road, Auckland, 1730, New Zealand P +64 9 272 2730 F +64 9 272 2733 information@mirotone.co.nz Mirotone (Thailand) Co., Ltd

83 Moo 4, Poochaosamingprai Rd, Samrong Klang, Prapradaeng, Samutprakam, 10130, Thailand P +66 2 754 4451 F +66 2 754 4450

www.mirotone.com