

## STRIPCOAT 3520

A temporary coating designed to provide a removable protective film to the inside of galvanised steel spray booths. This film can be easily removed to reduce unwanted overspray build up reducing the risk of dust contamination and the risk of fire.

### Product Advantages

- Fast drying
- White in colour, provides good light reflection when applied to internal spray booths
- Dries to a strippable film when applied at the correct wet film thickness
- Dries to a white flexible film

**Typical Applications** Galvanised steel spray booths only

**Coverage:** 5 m<sup>2</sup> per litre

**Thinning:** MIROSOL 1222

**Application Viscosity:** 18-23 seconds BS4 Flow Cup at 25°C.

**Wet Film Thickness (WFT):** 150-175 microns per coat. Can be achieved in multiple coats.

### Application Methods:

Suction Gun:	Use 1.5 to 2mm (59-79 thou) orifice with 350-400kpa (50-55 psi).
Pressure Pot:	Use 1.5 to 2mm (59-79 thou) orifice with pressure pot air-cap. Gun pressure 350-400kpa (50-55 psi) and a pot pressure of 45kpa (6 psi) max.
Airless Spray:	Use 0.23 to 0.33mm (9-13 thou) orifice, 15cm fan (dependent on job) with regulated pump pressure of 350-400kpa (50-55 psi).
Air Mix Guns:	Settings similar to airless spray with the air-assisted regulator pressure at 70-90kpa (10-15psi).

Clean steel with MIROSOL 1231 Wax & Grease Remover before applying STRIPCOAT 3520.

**Drying:** Touch Dry: 5 minutes  
Hard Dry: Overnight

**Application Equipment Clean Up:** Clean all equipment using MIROSOL 1222 or 1286 Thinner

**Shelf Life:** 24 months

**Packaging:** 20 litres

## Health & Safety

Before handling, refer to the Material Safety Data Sheet for health and safety information. Ensure that all personnel using this product have read and understood this data sheet and the associated MSDS and packaging label before using this product.

---

**Mirotone Pty Ltd Australia (Head Office)**

ABN 40 000 041 136  
21 Marigold Street,  
Revesby NSW 2212 Australia  
P +61 2 9795 3700 F +61 2 9771 3601  
sales@mirotone.com.au

**Mirotone (NZ) Ltd New Zealand (Head Office)**

32 Cryers Road,  
Auckland, 1730, New Zealand  
P +64 9 272 2730 F +64 9 272 2733  
information@mirotone.co.nz

**Mirotone (Thailand) Co., Ltd**

83 Moo 4, Poochaosamingprai Rd,  
Samrong Klang, Prapadaeng,  
Samutprakam, 10130, Thailand  
P +66 2 754 4451 F +66 2 754 4450

**[www.mirotone.com](http://www.mirotone.com)**